

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 2 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

Amendments to the Claims


This listing of claims replaces all prior versions, and listings, of claims in the above-identified application:

1. **(Previously Presented)** A polymerizable dental composition suitable for use in the oral environment comprising:

an ethylenically unsaturated compound;

a dental additive; and


an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation selected from:

1) a phosphorus-containing cation of Formula III:



III

where each R^2 is independently an unsubstituted alkyl, an alkyl substituted with a hydroxy, an unsubstituted aryl, an aryl substituted with an alkyl, hydroxy, or combinations thereof; or

2) a nitrogen-containing cation having a ring structure comprising a 4 to 12 member heterocyclic group having a positively charged nitrogen atom, said heterocyclic being saturated or unsaturated and having up to 3 heteroatoms selected from oxygen, sulfur, nitrogen, or combinations thereof, wherein said ring structure is unsubstituted or substituted with a substituent selected from an alkyl, aryl, acyl, alkoxy, aryloxy, halo,

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 3 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

mercapto, amino, hydroxy, azo, cyano, carboxy, alkoxycarbonyl,
aryloxycarbonyl, halocarbonyl, or combinations thereof,

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar¹ is a C₆₋₃₀ aryl or a C₃₋₃₀ heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group.

2. **(Previously Presented)** The polymerizable dental composition of claim 1 wherein the dental additive is selected from the group consisting of fluoride sources, whitening agents, anticaries agents, remineralizing agents, enzymes, breath fresheners, anesthetics, clotting agents, acid neutralizers, chemotherapeutic agents, immune response modifiers, medicaments, indicators, dyes, pigments, wetting agents, surfactants, buffering agents, viscosity modifiers, thixotropes, fillers, polyols, antimicrobial agents, antifungal agents, stabilizers, agents for treating xerostomia, desensitizers, and combinations thereof.
3. **(Original)** The polymerizable dental composition of claim 1 wherein the dental additive is a photobleachable dye.
4. **(Original)** The polymerizable dental composition of claim 1 wherein the composition is in a form selected from the group consisting of a dispersion, a suspension, an emulsion, a solution, and combinations thereof.
5. **(Original)** The polymerizable dental composition of claim 1 wherein the composition is a primer, a dental adhesive, an orthodontic adhesive, a coating, a sealant, a cement, a restorative, or combinations thereof.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 4 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

6. (Original) The polymerizable dental composition of claim 1 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
7. (Original) The polymerizable dental composition of claim 6 wherein the sensitizer is selected from the group consisting of camphorquinone, benzil, furil, 3,3,6,6-tetramethylcyclohexanedione, phenanthraquinone, 1-phenyl-1,2-propanedione, and combinations thereof.
8. (Original) The polymerizable dental composition of claim 1 wherein the initiator system further comprises an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode.
9. (Original) The polymerizable dental composition of claim 8 wherein the electron acceptor is an iodonium salt, a hexaarylbiimidazole, a persulfate, a peroxide, a metal ion in an oxidized state, or combinations thereof.
10. (Original) The polymerizable dental composition of claim 8 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
11. (Original) The polymerizable dental composition of claim 1 wherein the initiator system further comprises a reducing agent different from the arylsulfinate salt.
12. (Previously Presented) A polymerizable composition comprising:
an ethylenically unsaturated compound; and
an initiator system comprising an arylsulfinate salt having an anion of Formula I


Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 5 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003


For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS



I

and a cation selected from:

- 1) a phosphorus-containing cation of Formula III:



III

where each R^2 is independently an unsubstituted alkyl, an alkyl substituted with a hydroxy, an unsubstituted aryl, an aryl substituted with an alkyl, hydroxy, or combinations thereof; or

- 2) a nitrogen-containing cation having a ring structure comprising a 4 to 12 member heterocyclic group having a positively charged nitrogen atom, said heterocyclic being saturated or unsaturated and having up to 3 heteroatoms selected from oxygen, sulfur, nitrogen, or combinations thereof, wherein said ring structure is unsubstituted or substituted with a substituent selected from an alkyl, aryl, acyl, alkoxy, aryloxy, halo, mercapto, amino, hydroxy, azo, cyano, carboxy, alkoxycarbonyl, aryloxycarbonyl, halocarbonyl, or combinations thereof,

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

wherein the polymerizable composition is a dental material suitable for use in the oral environment.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 6 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

13. (Original) The polymerizable composition of claim 12 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
14. (Original) The polymerizable composition of claim 12 wherein the initiator system further comprises an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode.
15. (Original) The polymerizable composition of claim 14 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
16. (Original) The polymerizable composition of claim 12 wherein the initiator system further comprises a reducing agent different from the arylsulfinate salt.
17. (Original) The polymerizable composition of claim 12 further comprising a photobleachable dye.
18. (Withdrawn - Currently Amended) A method of hardening a composition comprising irradiating a polymerizable dental composition suitable for use in the oral environment and comprising:
- an ethylenically unsaturated compound;
 - a dental additive;
 - a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers; and
 - an initiator system comprising an arylsulfinate salt having an anion of Formula I


Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 7 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003


For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS



I

and a cation selected from:

- 1) a phosphorus-containing cation of Formula III:



III

where each R^2 is independently an unsubstituted alkyl, an alkyl substituted with a hydroxy, an unsubstituted aryl, an aryl substituted with an alkyl, hydroxy, or combinations thereof; or

- 2) a nitrogen-containing cation having a ring structure comprising a 4 to 12 member heterocyclic group having a positively charged nitrogen atom, said heterocyclic being saturated or unsaturated and having up to 3 heteroatoms selected from oxygen, sulfur, nitrogen, or combinations thereof, wherein said ring structure is unsubstituted or substituted with a substituent selected from an alkyl, aryl, acyl, alkoxy, aryloxy, halo, mercapto, amino, hydroxy, azo, cyano, carboxy, alkoxycarbonyl, aryloxy carbonyl, halocarbonyl, or combinations thereof,

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 8 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

19. (Withdrawn) The method of claim 18 wherein the sensitizer is selected from the group consisting of camphorquinone, benzil, furil, 3,3,6,6-tetramethylcyclohexanedione, phenanthraquinone, 1-phenyl-1,2-propanedione, and combinations thereof.

20. (Withdrawn) The method of claim 18 wherein the polymerizable dental composition further comprises an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode.

21. (Withdrawn - Currently Amended) A method of hardening a polymerizable dental composition suitable for use in the oral environment comprising:

combining components to form a hardenable dental composition; and


allowing the dental composition to harden, wherein the components comprise:

an ethylenically unsaturated compound;

a dental additive;


an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



and a cation selected from:

1) a phosphorus-containing cation of Formula III:



Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 9 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

where each R^2 is independently an unsubstituted alkyl, an alkyl substituted with a hydroxy, an unsubstituted aryl, an aryl substituted with an alkyl, hydroxy, or combinations thereof; or

- 2) a nitrogen-containing cation having a ring structure comprising a 4 to 12 member heterocyclic group having a positively charged nitrogen atom, said heterocyclic being saturated or unsaturated and having up to 3 heteroatoms selected from oxygen, sulfur, nitrogen, or combinations thereof, wherein said ring structure is unsubstituted or substituted with a substituent selected from an alkyl, aryl, acyl, alkoxy, aryloxy, halo, mercapto, amino, hydroxy, azo, cyano, carboxy, alkoxycarbonyl, aryloxycarbonyl, halocarbonyl, or combinations thereof,

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group.

22. **(Withdrawn)** The method of claim 21 wherein the electron acceptor is an iodonium salt, a hexaarylbisimidazole, a persulfate, a peroxide, a metal ion in an oxidized state, or combinations thereof.

23. **(Withdrawn)** The method of claim 21 wherein the components further comprise a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.

24. **(Withdrawn)** The method of claim 23 wherein the method further comprises irradiating the hardenable dental composition.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 10 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

25. (Withdrawn - Currently Amended) A method of treating a dental structure surface comprising:

applying a hardenable dental composition to the dental structure surface; and


irradiating the dental composition,

wherein the hardenable dental composition comprises:

an ethylenically unsaturated compound;

a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers; and


an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation selected from:

- 1) a phosphorus-containing cation of Formula III:



III

where each R^2 is independently an unsubstituted alkyl, an alkyl substituted with a hydroxy, an unsubstituted aryl, an aryl substituted with an alkyl, hydroxy, or combinations thereof; or

- 2) a nitrogen-containing cation having a ring structure comprising a 4 to 12 member heterocyclic group having a positively charged nitrogen atom, said heterocyclic being saturated or unsaturated and having up to 3 heteroatoms selected from oxygen, sulfur, nitrogen, or combinations thereof, wherein said ring structure is unsubstituted or substituted with a substituent selected from an alkyl, aryl, acyl, alkoxy, aryloxy, halo,

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 11 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

mercapto, amino, hydroxy, azo, cyano, carboxy, alkoxycarbonyl,
aryloxycarbonyl, halocarbonyl, or combinations thereof,

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar¹ is a C₆₋₃₀ aryl or a C₃₋₃₀ heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

wherein the hardenable dental composition is a polymerizable dental material suitable for use in the oral environment.

26. **(Withdrawn)** The method of claim 25 wherein the hardenable dental composition further comprises a dental additive.

27. **(Withdrawn)** The method of claim 25 wherein the sensitizer is selected from the group consisting of camphorquinone, benzil, furil, 3,3,6,6-tetramethylcyclohexanedione, phenanthraquinone, 1-phenyl-1,2-propanedione, and combinations thereof.

28. **(Withdrawn)** The method of claim 25 wherein the hardenable dental composition further comprises an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode.

29. **(Withdrawn - Currently Amended)** A method of treating a dental structure surface comprising:

applying a hardenable dental composition to the dental structure surface; and

allowing the hardenable dental composition to harden,

wherein the dental composition comprises:

an ethylenically unsaturated compound;

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 12 of 33

Serial No.: 10/672,814


Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode; and


an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation selected from:

- 1) a phosphorus-containing cation of Formula III:



III

where each R^2 is independently an unsubstituted alkyl, an alkyl substituted with a hydroxy, an unsubstituted aryl, an aryl substituted with an alkyl, hydroxy, or combinations thereof; or

- 2) a nitrogen-containing cation having a ring structure comprising a 4 to 12 member heterocyclic group having a positively charged nitrogen atom, said heterocyclic being saturated or unsaturated and having up to 3 heteroatoms selected from oxygen, sulfur, nitrogen, or combinations thereof, wherein said ring structure is unsubstituted or substituted with a substituent selected from an alkyl, aryl, acyl, alkoxy, aryloxy, halo, mercapto, amino, hydroxy, azo, cyano, carboxy, alkoxycarbonyl, aryloxycarbonyl, halocarbonyl, or combinations thereof,

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 13 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

wherein the hardenable dental composition is a polymerizable dental material suitable for use in the oral environment.

30. **(Withdrawn)** The method of claim 29 wherein the hardenable dental composition further comprises a dental additive.

31. **(Withdrawn)** The method of claim 29 wherein the electron acceptor is an iodonium salt, a hexaarylbisimidazole, a persulfate, a peroxide, a metal ion in an oxidized state, or combinations thereof.

32. **(Withdrawn)** The method of claim 29 wherein the hardenable dental composition further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.


33. **(Withdrawn)** The method of claim 32 wherein the method further comprises irradiating the hardenable dental composition.

34. **(Withdrawn - Currently Amended)** A self-etching, polymerizable dental composition comprising:

an ethylenically unsaturated compound with acid functionality;

an ethylenically unsaturated compound without acid functionality; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation selected from:

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 14 of 33


Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

- 1) a phosphorus-containing cation of Formula III:



III

where each R^2 is independently an unsubstituted alkyl, an alkyl substituted with a hydroxy, an unsubstituted aryl, an aryl substituted with an alkyl, hydroxy, or combinations thereof; or

- 2) a nitrogen-containing cation having a ring structure comprising a 4 to 12 member heterocyclic group having a positively charged nitrogen atom, said heterocyclic being saturated or unsaturated and having up to 3 heteroatoms selected from oxygen, sulfur, nitrogen, or combinations thereof, wherein said ring structure is unsubstituted or substituted with a substituent selected from an alkyl, aryl, acyl, alkoxy, aryloxy, halo, mercapto, amino, hydroxy, azo, cyano, carboxy, alkoxycarbonyl, aryloxycarbonyl, halocarbonyl, or combinations thereof,

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

wherein the polymerizable composition is a dental material suitable for use in the oral environment.

35. (Withdrawn) The self-etching, polymerizable dental composition of claim 34 wherein the composition is a primer, a dental adhesive, an orthodontic adhesive, a coating, a sealant, a cement, a restorative, or combinations thereof.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 15 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

36. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 34 wherein the composition is non-aqueous.
37. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 34 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
38. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 34 wherein the initiator system further comprises an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode.
39. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 38 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
40. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 34 wherein the composition further comprises a filler.
41. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 40 wherein the filler is a nanofiller.
42. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 34 wherein the acid functionality comprises carboxylic acid functionality, phosphoric acid functionality, sulfonic acid functionality, or combinations thereof.
43. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 34 further comprising a photobleachable dye.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 16 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

44. **(Withdrawn - Currently Amended)** A self-etching, polymerizable dental composition comprising:


an ethylenically unsaturated compound with acid functionality;

an ethylenically unsaturated compound without acid functionality

a surfactant;

water; and


an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation having selected from:

1) a phosphorus-containing cation of Formula III:



III

where each R^2 is independently an unsubstituted alkyl, an alkyl substituted with a hydroxy, an unsubstituted aryl, an aryl substituted with an alkyl, hydroxy, or combinations thereof; or

2) a nitrogen-containing cation having a ring structure comprising a 4 to 12 member heterocyclic group having a positively charged nitrogen atom, said heterocyclic being saturated or unsaturated and having up to 3 heteroatoms selected from oxygen, sulfur, nitrogen, or combinations thereof, wherein said ring structure is unsubstituted or substituted with a substituent selected from an alkyl, aryl, acyl, alkoxy, aryloxy, halo,

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 17 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

mercapto, amino, hydroxy, azo, cyano, carboxy, alkoxycarbonyl,
aryloxycarbonyl, halocarbonyl, or combinations thereof,

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar¹ is a C₆₋₃₀ aryl or a C₃₋₃₀ heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

wherein the self-etching, polymerizable dental composition is an emulsion suitable for use in the oral environment.

45. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 44 wherein the emulsion is a water-in-oil emulsion.

46. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 44 wherein the emulsion is physically stable.

47. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 44 wherein the composition comprises less than 30% by weight water.

48. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 44 wherein the composition is a water-in-oil micro-emulsion.

49. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 44 wherein the composition further comprises a filler.

50. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 49 wherein the filler is a nanofiller.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 18 of 33


Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

51. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 44 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
52. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 44 wherein the initiator system further comprises an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode.
53. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 52 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
54. **(Withdrawn)** The self-etching, polymerizable dental composition of claim 44 further comprising a photobleachable dye.
55. **(Withdrawn - Currently Amended)** A self-adhesive, polymerizable dental composition comprising:
- an ethylenically unsaturated compound with acid functionality;
 - an ethylenically unsaturated compound without acid functionality;
 - at least 40% by weight filler; and
 - an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation selected from:

- 1) a phosphorus-containing cation of Formula III:


Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 19 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS



III

where each R^2 is independently an unsubstituted alkyl, an alkyl substituted with a hydroxy, an unsubstituted aryl, an aryl substituted with an alkyl, hydroxy, or combinations thereof; or

- 2) a nitrogen-containing cation having a ring structure comprising a 4 to 12 member heterocyclic group having a positively charged nitrogen atom, said heterocyclic being saturated or unsaturated and having up to 3 heteroatoms selected from oxygen, sulfur, nitrogen, or combinations thereof, wherein said ring structure is unsubstituted or substituted with a substituent selected from an alkyl, aryl, acyl, alkoxy, aryloxy, halo, mercapto, amino, hydroxy, azo, cyano, carboxy, alkoxycarbonyl, aryloxycarbonyl, halocarbonyl, or combinations thereof,

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

wherein the polymerizable composition is a dental material suitable for use in the oral environment.

56. (Withdrawn) The self-adhesive, polymerizable dental composition of claim 55 wherein the composition is non-aqueous.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 20 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

57. **(Withdrawn)** The self-adhesive, polymerizable dental composition of claim 55 wherein the acid functionality comprises carboxylic acid functionality, phosphoric acid functionality, sulfonic acid functionality, or combinations thereof.
58. **(Withdrawn)** The self-adhesive, polymerizable dental composition of claim 55 wherein the filler is a nanofiller.
59. **(Withdrawn)** The self-adhesive, polymerizable dental composition of claim 55 further comprising a photobleachable dye.
60. **(Withdrawn)** The self-adhesive, polymerizable dental composition of claim 55 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
61. **(Withdrawn)** The self-adhesive, polymerizable dental composition of claim 55 wherein the initiator system further comprises an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode.
62. **(Withdrawn)** The self-adhesive, polymerizable dental composition of claim 61 wherein the initiator system further comprises a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers.
63. **(Previously Presented)** The polymerizable dental composition of claim 2 wherein the anticaries agent comprises xylitol.
64. **(Previously Presented)** The polymerizable dental composition of claim 2 wherein the remineralizing agent comprises a calcium phosphate compound.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 21 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003


For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

65. **(Previously Presented)** A polymerizable dental composition suitable for use in the oral environment comprising:

an ethylenically unsaturated compound;


a dental additive; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation of Formula II:



II


where R^1 and each R^4 are independently alkyl groups having at least 3 carbon atoms, and

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group.

66. **(Previously Presented)** A polymerizable composition comprising:

an ethylenically unsaturated compound; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation of Formula II:


Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 22 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS



II

where R^1 and each R^4 are independently alkyl groups having at least 3 carbon atoms, and

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

whercin the polymerizable composition is a dental material suitable for use in the oral environment.


67. (Withdrawn - Currently Amended) A method of hardening a composition comprising irradiating a polymerizable dental composition suitable for use in the oral environment and comprising:

an ethylenically unsaturated compound;

a dental additive;


a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation of Formula II:



Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 23 of 33

Serial No.: 10/672,814

Confirmation No.: 8914


Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

II


where R^1 and each R^4 are independently alkyl groups having at least 3 carbon atoms, and
 wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group.

68. **(Withdrawn - Currently Amended)** A method of hardening a composition comprising:
 combining components to form a hardenable dental composition; and
 allowing the dental composition to harden, wherein the components comprise:
 an ethylenically unsaturated compound;
 a dental additive;
 an electron acceptor having a reduction potential in N,N-dimethylformamide of
 +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode; and
an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation of Formula II:



II

where R^1 and each R^4 are independently alkyl groups having at least 3 carbon atoms, and
 wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 24 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

C₃₋₃₀ heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and
wherein the hardenable dental composition is a polymerizable dental composition suitable for use in the oral environment.

69. (Withdrawn - Currently Amended) A method of treating a dental structure surface comprising:


applying a hardenable dental composition to the dental structure surface; and
 irradiating the dental composition,

wherein the hardenable dental composition comprises:

an ethylenically unsaturated compound;


a sensitizer capable of absorbing a wavelength of actinic radiation in the range of 250 to 1000 nanometers; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation of Formula II:



II

where R¹ and each R⁴ are independently alkyl groups having at least 3 carbon atoms, and

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar¹ is a C₆₋₃₀ aryl or a C₃₋₃₀ heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 25 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

wherein the hardenable dental composition is a polymerizable dental material suitable for use in the oral environment.

70. (Withdrawn - Currently Amended) A method of treating a dental structure surface comprising:

applying a hardenable dental composition to the dental structure surface; and


allowing the hardenable dental composition to harden,

wherein the dental composition comprises:

an ethylenically unsaturated compound;


an electron acceptor having a reduction potential in N,N-dimethylformamide of +0.4 to -1.0 volts versus a silver/silver nitrate reference electrode; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation of Formula II:



II

where R^1 and each R^4 are independently alkyl groups having at least 3 carbon atoms, and

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

wherein the hardenable dental composition is a polymerizable dental material suitable for use in the oral environment.

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 26 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003


For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS

71. **(Withdrawn - Currently Amended)** A self-etching, polymerizable dental composition comprising:

an ethylenically unsaturated compound with acid functionality;


an ethylenically unsaturated compound without acid functionality; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation of Formula II:



II

where R^1 and each R^4 are independently alkyl groups having at least 3 carbon atoms, and

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

wherein the polymerizable composition is a dental material suitable for use in the oral environment.

72. **(Withdrawn - Currently Amended)** A self-etching, polymerizable dental composition comprising:

an ethylenically unsaturated compound with acid functionality;

an ethylenically unsaturated compound without acid functionality

a surfactant;

Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 27 of 33

Serial No.: 10/672,814


Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS


water; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation of Formula II:



II

where R^1 and each R^4 are independently alkyl groups having at least 3 carbon atoms, and

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

wherein the self-etching, polymerizable dental composition is an emulsion suitable for use in the oral environment.


73. (Withdrawn - Currently Amended) A self-adhesive, polymerizable dental composition comprising:

an ethylenically unsaturated compound with acid functionality;

an ethylenically unsaturated compound without acid functionality;

at least 40% by weight filler; and

an initiator system comprising an arylsulfinate salt having an anion of Formula I



I

and a cation of Formula II:


Amendment and Response Under 37 C.F.R. §1.116 - Expedited Examining Procedure Page 28 of 33

Serial No.: 10/672,814

Confirmation No.: 8914

Filed: 26 September 2003

For: DENTAL COMPOSITIONS AND METHODS WITH ARYLSULFINATE SALTS



II

where R^1 and each R^4 are independently alkyl groups having at least 3 carbon atoms, and

wherein the arylsulfinate salt has an oxidation potential in N,N-dimethylformamide of 0.0 to +0.4 volts versus a silver/silver nitrate reference electrode, and wherein Ar^1 is a C_{6-30} aryl or a C_{3-30} heteroaryl that is unsubstituted or substituted with an electron withdrawing group or an electron withdrawing group in combination with an electron donating group, and

wherein the polymerizable composition is a dental material suitable for use in the oral environment.